

**Rhenocoll Fassadenfarbe AF 50**, high quality façade paint, white

**Rhenocoll Fassadenfarbe AF 50**, façade paint, different colors

**Rhenocoll Fassadenfarbe AF 50**, base A and C

Art.-No.: A 5700 (Fassadenfarbe, weiß - façade paint, white)

Art.-No.: A 5703 (Bunttöne-Store – color tone-store)

Art.-No.: A 5705 (Color Mix)

Art.-No.: A 5707 (Basis A – base A), A 5709 (Basis C – base C)

**Specification:** High quality facade paint for above average aging and UV-resistant facade coatings. For professional use. White, elastic, permeable. Absolutely weather resistant in all climatic zones, impact rain proof and good coverage. Environmentally friendly, water-based.


**Color tone:** White, color tone-store, color tone in color-mix system from base paints

**Applications / Surface:** For exterior use, plaster, concrete, masonry, mineral surfaces. For renovation requirements of stable and matt dispersion coatings.

**Yield:** Approx. 7 m<sup>2</sup> / liter for one coat. For fine-plastic coatings, determine the consumption by trial coating.

**VOC 2010:** Cat. C / base Wb / max. value 40g/L / actual value 34 g/L

**Preservation:** Our specific raw material selection makes the conventional equipment against bacteria, mold, fungi, and putrefactive agents unnecessary.

Self-immunizing	❖	Natural	❖	Mineral
<ul style="list-style-type: none"> <li>✓ Designed for professional use</li> <li>✓ No carcinogenic ingredients</li> <li>✓ Free of Isothiazolones – free of microplastics</li> <li>✓ Totally harmless to humans and animals</li> <li>✓ Acts as an active protection of the environment, water, soil by conscious avoidance of toxic substances</li> <li>✓ Protected by a worldwide patent</li> </ul>				 <p>Protective shield the natural immunization</p>

**Technical information:**

Application: By brush, roll or spraying equipment  
 Coating of the facade: 2 - 3 coats recommended, according to weather conditions  
 3 coats are recommended when exposed to strong weathering  
 Processing temperature: Not below +8°C (material, surrounding and room temperature)  
 Drying time: At 20°C and rel. Humidity of 65%:  
 Can be recoated after 5-6 hours of drying time. Rainproof after 8 hours. These times are prolonged at lower temperatures and higher humidity  
 Tool cleaning: Immediately after usage with water  
 General note: Stir before usage and after longer breaks, do not mix with solvent-based products  
 Tinting: With compatible full-tone and tinting colors

**Processing:** The base coat has to be clean, dry, oil / grease-free and bearing. Non-bearing and flaking surfaces have to be removed. Note VOB, part C, DIN 18363, paragraph 3. Distemper and chalking surfaces must be completely washed off. Plaster has to dry thoroughly for at least 4 weeks. Prime absorbing and critical surfaces with facade protection ground Rhenocoll Fassadenschutzgrund 12 F.

Primer coat: Can be diluted with water up to maximum 10 %.

Finishing coat: Rhenocoll Fassadenfarbe AF 50 – use undiluted.

Spray application: Adjust product to spray viscosity.

**Labeling according (EG) No. 1272/2008:** No labeling required.

**ADR/GGVS:** Non dangerous goods.

**Declaration of the HealthPaint ingredients:** Calcium carbonate, quartz sand, titanium dioxide, kaolin, talcum, barite powder, water, aqueous dispersion, mixture of minerals.

**Safety notes:** During processing, common protection measures and regulations according to the authorized trade association must be observed. Safety-relevant data and instructions regarding disposal can be found in the safety data sheet. For professional use.

**Storage:** In original container and not below +8°C Do not store or transport above + 30 ° C for longer periods of time. Re-close firmly. Can be stored for 12 months in un-opened original container. Use product quickly, once container has been opened.

**Supply units:**

2,5 l pail

5 l pail

10 l pail

12,5 l pail

**Service:**

Our service team for application technology is available to you at any time without obligation.

**Phone:** ++49 (0)6384 99 38 - 0

**Fax:** ++49 (0)6384 99 38 - 112

**Email:** [info@rhenocoll.de](mailto:info@rhenocoll.de)

The information given within is without obligation and is based on practical experience as well as on experiments which we have carried out and are not attribute guaranties in the sense of the newest BGH legal requirements. We recommend that in any case users carry out their own tests since we have no influence over the large diversity of materials and their processing. No liability for the manufacturer can be derived from the contents of this data sheet. Statements going beyond or deviating from the contents of this data sheet require the written confirmation of the company headquarters. Our General Terms & Conditions apply in any case. With the release of this Technical Data Sheet all previous versions become obsolete.