

Rhenoplast HR 2 (VP6465)

Industrial bonding cleaner

Art.-No.: A 7808

Specification: Solvent cleaner, nearly odorless, improves the adhesion for better overcoat ability of uPVC parts. It contains an antistatic agent to reduce the static charge on uPVC surfaces. Suitable to clean hard uPVC surfaces, especially window profiles. Adhesive bridges are built up in the uPVC for a better bonding of the subsequent coating to the substrate of Rhenoplast KP 1+ (plastic profile lacquer). For professional use.

Processing: Spray Rhenoplast HR2 undiluted or apply with a cloth to clean the parts to be coated, after approx. 1 Min. air blow the surface or leave to air dry. Process at room temperature, do not heat the cleaner. The profile surface has to be completely dry before coating.

Consumption: 15- 20 g/m2.

Color: colorless

Storage: Cool, frost-free, close once-opened container well. Can be stored for up to 1 year.

VOC 2010: not applicable

Labeling according to regulation (EC) No. 1272/2008: please note safety data sheet

Transportation: GGVS/ADR: no dangerous goods

Safety notes: During processing, common protection measures and regulations according to the authorized trade association must be observed. Safety-relevant data and instructions regarding disposal can be found in the safety data sheet.

Wear safety gloves. Wear eye protection. Wash hand thoroughly after use. In case of contact with eyes rinse carefully with water for several minutes. If eye irritation persists consult a specialist.

Supply form:

- 1 l plastic bottle
- 5 l canister
- 30 l hobbock

Service:

Our service team for application technology is available to you at any time without obligation.

Phone: ++49 (0)6384 99 38 - 0

Fax: ++49 (0)6384 99 38 - 112

Email: info@rhenocoll.de

The information given within is without obligation and is based on practical experience as well as on experiments which we have carried out and are not attribute guaranties in the sense of the newest BGH legal requirements. We recommend that in any case users carry out their own tests since we have no influence over the large diversity of materials and their processing. No liability for the manufacturer can be derived from the contents of this data sheet. Statements going beyond or deviating from the contents of this data sheet require the written confirmation of the company headquarters. Our General Terms & Conditions apply in any case. With the release of this Technical Data Sheet all previous versions become obsolete.