

## Rhenocoll Fassadenschutzgrund 12 F, colorless, primer

For exterior use

Art.-No.: A 5730

**Specification:** Colorless safety-primer for exterior use. For absorbent substrates with particularly good penetration properties for solidifying highly chalky or sandy underlying surfaces. Suitable for all gypsum-containing surfaces, ready-mixed plaster, fiber cement, for limestone and hard brick, masonry as clinker. In the case of new gypsum surfaces, and normal application thickness, it is not necessary to sand the sinter skin (surface peeling skin). Ideally suited for interiors and rooms of the food sector. Solvent- and odor-free. Environmentally friendly, water-based. Not suitable for non-absorbent subsoils.

**Application:** By brush/roller.


**Supply form:** Nearly colorless.

**Substrate:** For absorbent surfaces, plaster, fiber cement, masonry.

**Further treatment:** Wall and facade paints.

**VOC 2010:** Cat H / base Wb / max value 30g/L / actual value 20g/L

**Preservation:** Our specific raw material selection makes the conventional equipment against bacteria, mold, fungi, and putrefactive agents unnecessary.

Self-immunizing	❖	Natural	❖	Mineral
<ul style="list-style-type: none"><li>✓ Designed for professional use</li><li>✓ No carcinogenic ingredients</li><li>✓ Free of Isothiazolones – free of microplastics</li><li>✓ Totally harmless to humans and animals</li><li>✓ Acts as an active protection of the environment, water, soil by conscious avoidance of toxic substances</li><li>✓ Protected by a worldwide patent</li></ul>				 <p>Protective shield the natural immunization</p>

### Technical information:

Processing: Undiluted  
Processing temperature: Not below 8°C (material and room temperature)  
Consumption: Approx. 10m<sup>2</sup> per liter depending on application strength.  
Drying time: At +20 °C und 65 % rel. humidity, re-coatable after 1 hour. completely dried after 1 day. At lower temperatures and higher humidity, these times are extended.  
General note: Stir well before use and after longer periods of non-use. Do not mix with solvent-based materials.  
Flashpoint: None

**Coating construction:** Preliminary work. The substrate must be clean, dry, free from dirt and dust. Note: VOB, part C, DIN 18363, paragraph 3.

**Labeling according (EG) No. 1272/2008:** No labeling required

**ADR/GGVS:** Non dangerous goods

**Safety notes:** During processing, common protection measures and regulations according to the authorized trade association must be observed. Safety-relevant data and instructions regarding disposal can be found in the safety data sheet. For professional use.

**Storage:** In original container and not below +8°C Do not store or transport above + 30 ° C for longer periods of time. Re-close firmly. Can be stored for 12 months in un-opened original container. Use product quickly, once container has been opened.

**Supply units:**

2,5 Liter canister  
5 Liter canister  
10 Liter canister  
25 Liter canister

**Service:**

Our service team for application technology is available to you at any time without obligation.

**Phone:** ++49 (0)6384 99 38 - 0

**Fax:** ++49 (0)6384 99 38 - 112

**Email:** [info@rhenocoll.de](mailto:info@rhenocoll.de)

The information given within is without obligation and is based on practical experience as well as on experiments which we have carried out and are not attribute guaranties in the sense of the newest BGH legal requirements. We recommend that in any case users carry out their own tests since we have no influence over the large diversity of materials and their processing. No liability for the manufacturer can be derived from the contents of this data sheet. Statements going beyond or deviating from the contents of this data sheet require the written confirmation of the company headquarters. Our General Terms & Conditions apply in any case. With the release of this Technical Data Sheet all previous versions become obsolete.