

Rhenocoll Lackleim N

Art. No.: A 1121

Specifications:

Rhenocoll Lackleim N is a ready-to-use 1-component dispersion glue with good adhesion on common surfaces. Lackleim N is transparent when dry, has a high joint stability with a special elasticity. Rhenocoll Lackleim N has best adhesion on to surfaces coated with NC lacquer. Lackleim N is moisture-resistant and elastic. For professional use.

Recommended processing conditions:

Application amount : ca. 130 g/m²
Processing : Brush, spatula, roller
Processing temperature : 18 – 20° C recommended
Wood moisture : 8 - 12 % maximum
Bonding pressure : 2-5 kp/cm²
Open time : 5-10 minutes (depending on room temperature), influenced by application amount, humidity and absorption capacity
Press time : 4 – 6 minutes at 20°C. Press time shortens through warm pressing or preheating on one side.

Sanding the surface improves the surface adhesion, especially on hardened varnishes.

Follow-up treatment:

After hardening for 2-3 hours.

Storage:

6 months in closed container; protect from frost; do not bring into contact with iron.

Labeling:

No labeling required.

Supply form:

750 g can (16 units in one box)
6 kg pail
12 kg pail
32 kg hobbock

Service:

Our service team for application technology is available to you at any time without obligation.

Phone: ++49 (0)6384 99 38 - 0

Fax: ++49 (0)6384 99 38 - 112

Email: info@rhenocoll.de

The information given within is without obligation and is based on practical experience as well as on experiments which we have carried out and are not attribute guaranties in the sense of the newest BGH legal requirements. We recommend that in any case

users carry out their own tests since we have no influence over the large diversity of materials and their processing. No liability for the manufacturer can be derived from the contents of this data sheet. Statements going beyond or deviating from the contents of this data sheet require the written confirmation of the company headquarters. Our General Terms & Conditions apply in any case.

With the release of this Technical Data Sheet all previous versions become obsolete.